Serial No.: 10/716,543

Filed: November 20, 2003

Page : 2 of 10

Amendments to the Claims

This listing of claims replaces all prior versions and listings of claims in the application.

Listing of Claims

1. (Withdrawn) A fuse comprising:

an electrical assembly comprising two electrical contacts accessible from an exterior of a fuse and a fuse element in contact with the two electrical contacts; and

a fuse tube assembly comprising a pre-formed tubular support structure surrounding at least a portion of the electrical assembly and a reinforcing structure formed over the pre-formed tubular support structure after the pre-formed tubular support structure is formed, the reinforcing structure being in contact with at least a portion of the electrical assembly, wherein the reinforcing structure comprises a fiber matrix pre-impregnated with a resin.

- 2. (Withdrawn) The fuse of claim 1 wherein the fuse comprises a current limiting fuse.
- 3. (Withdrawn) The fuse of claim 1 wherein the fuse element extends between the contacts.
- 4. (Withdrawn) The fuse of claim 1 wherein the fuse tube assembly extends between the contacts.
- 5. (Withdrawn) The fuse of claim 1 wherein an inside surface of the pre-formed tubular support structure overlaps a portion of an outside surface of each of the electrical contacts.
- 6. (Withdrawn) The fuse of claim 1 wherein the fiber matrix comprises a pre-woven fabric.

Serial No.: 10/716,543

Filed: November 20, 2003

Page : 3 of 10

7. (Withdrawn) The fuse of claim 6 wherein the fibers in the pre-woven fabric are oriented in a predetermined orientation.

8. (Cancelled)

- 9. (Withdrawn) The fuse of claim 1 wherein the pre-formed tubular structure comprises a composite material.
- 10. (Withdrawn) The fuse of claim 1 wherein the pre-formed tubular structure has a slit extending from a first end of the structure to a second end of the structure.
- 11. (Withdrawn) The fuse of claim 1 wherein a thickness of the pre-formed tubular support structure is greater than a thickness of the reinforcing structure.
- 12. (Withdrawn) The fuse of claim 1 wherein the fuse tube assembly further comprises a heat shrink structure formed over the reinforcing structure.
- 13. (Withdrawn) The fuse of claim 12 wherein the heat shrink structure is constructed of a material providing UV protection.
- 14. (Withdrawn) The fuse of claim 12 wherein the heat shrink structure comprises a preformed sleeve.
- 15. (Withdrawn) The fuse of claim 12 wherein the heat shrink structure comprises one or more strips of a heat shrink tape.
- 16. (Withdrawn) The fuse of claim 1 wherein the fiber matrix is applied circumferentially.

Serial No.: 10/716,543

Filed: November 20, 2003

Page : 4 of 10

17. (Withdrawn) The fuse of claim 16 wherein the fiber matrix is applied circumferentially such that the fibers have a predetermined orientation at a predetermined angle with respect to an axis of the fuse.

- 18. (Withdrawn) The fuse of claim 1 wherein the fiber matrix is applied vertically.
- 19. (Withdrawn) The fuse of claim 18 wherein the vertical application comprises at least one piece of fiber matrix placed in a vertical orientation along an axis of the fuse.
- 20. (Withdrawn) The fuse of claim 18 wherein the vertical application comprises a single piece of fiber matrix placed in a vertical orientation along an axis of the fuse and having a sufficient width to cover the majority of an outer surface of the fuse.
- 21. (Withdrawn) The fuse of claim 1 wherein the reinforcing structure further comprises at least one layer of pre-impregnated fiber matrix applied circumferentially and at least one layer of pre-impregnated fiber matrix applied vertically.
- 22. (Withdrawn) The fuse of claim 1 wherein the reinforcing structure is configured to reinforce a selected portion of an area of the fuse along a lengthwise axis of the fuse.
- 23. (Withdrawn) The fuse of claim 22 wherein the selected portion of the area comprises less than all of the area.
- 24. (Withdrawn) The fuse of claim 22 wherein the selected portion of the area comprises an area excluding a portion of the outside surface of the electrical assembly.
 - 25. (Previously Presented) A method of reinforcing a fuse, the method comprising:

Serial No.: 10/716,543

Filed: November 20, 2003

Page : 5 of 10

providing an electrical assembly, the electrical assembly comprising two electrical contacts accessible from an exterior of a fuse and a fuse element in contact with the two electrical contacts;

surrounding at least a portion of the electrical assembly by a pre-formed tubular support structure;

after surrounding at least a portion of the electrical assembly by the pre-formed tubular support structure, applying a reinforcing structure over the pre-formed tubular support structure and in contact with at least a portion of the electrical assembly, wherein the reinforcing structure comprises a fiber matrix, the fiber matrix comprising fibers pre-impregnated with a resin.

- 26. (Original) The method of claim 25 further comprising applying a heat shrink structure over the reinforcing structure.
- 27. (Original) The method of claim 25 wherein applying the reinforcing structure comprises applying the pre-impregnated fiber matrix in a rolling operation.
- 28. (Original) The method of claim 25 wherein applying the reinforcing structure comprises applying the pre-impregnated fiber matrix in a wrapping operation.
- 29. (Original) The method of claim 25 wherein applying the reinforcing layer comprises circumferentially applying the pre-impregnated fiber matrix.
- 30. (Original) The method of claim 25 wherein applying the reinforcing layer comprises vertically applying the pre-impregnated fiber matrix.
- 31. (Original) The method of claim 25 further comprising performing post application processing of the fuse.

Serial No.: 10/716,543

Filed: November 20, 2003

Page : 6 of 10

32. (Original) The method of claim 31 wherein performing post application processing comprises curing.

- 33. (Original) The method of claim 32 wherein curing the reinforcing fuse comprises heating the fuse.
- 34. (Currently Amended) The method of claim 33 wherein the fuse is heated to between approximately 250° F and 400° F.
- 35. (Original) The method of claim 25 further comprising pre-heating the electrical assembly.
- 36. (Currently Amended) The method of claim 35 wherein the electrical assembly is preheated to between approximately 100° F and 200° F.
- 37. (Original) The method of claim 25 further comprising filling the fuse with an electrical arc quenching medium.

38. (Withdrawn) A fuse comprising:

an electrical assembly comprising two electrical contacts accessible from an exterior of the fuse and a fuse element in contact with the two electrical contacts; and

a fuse tube assembly comprising a pre-formed tubular support structure surrounding at least a portion of the electrical assembly and a reinforcing structure formed over the pre-formed tubular support structure after the pre-formed tubular support structure is formed;

wherein the reinforcing structure comprises a resin composition of discontinuous fibers arbitrarily dispersed in an epoxy.

Serial No.: 10/716,543

Filed : November 20, 2003

Page : 7 of 10

39. (Withdrawn) The fuse of claim 38 wherein the fuse comprises a current limiting fuse.